# STEIKO Frontlit

TECHNICAL DATA SHEET

| COATED FRONTLIT 510gsm | | |
|---|---|---|
| CHARACTERISTICS | DATA | TEST METHOD |
| **Weight** | 510gsm | ISO3801:1977 |
| **Polyester Fabric** | 1000x1000 denier<br>18x18 fd per inch | DIN60001/DIN EN ISO2060 |
| **Type of Coating** | PVC | N/A |
| **Tensile Strength** | 1800N/5cm (L) | ISO527/3:1995 |
| | 1800N/5cm (W) | |
| **Tear Strength** | 280N/5cm (L) | ISO4674/1:2003 |
| | 250N/5cm (W) | |
| **Adhesion Strength** | 60N/5cm | DIN53357:1982 |
| **Low Temperature** | -22°F / -30°C | ISO13934-1:1999 |
| **RF Weldable (Heat Sealable)** | YES | DIN53354 |

| | |
|---|---|
| **APPLICATIONS:** | Banners, Pole Banners, Billboards, Display Systems |
| **INK COMPATIBILITY:** | UV, Latex, Solvent, Eco-Solvent |

CERTIFIED FOR HP LATEX INKS