

<b>Description of commodity: Steiko PET Backlit Single side PET backlit 320gsm</b>			
<b>ITEM</b>	<b>DATA</b>	<b>UNIT</b>	<b>TEST METHOD</b>
<b>Fabric</b>	NO		DIN EN ISO2060
<b>Construction</b>		inch	DIN60001
<b>Total weight</b>	320	g/sq.m	DIN53352 BS3424 method5A
<b>Weight of PET</b>	175	g/sq.m	DIN53352 BS3424 method5B
<b>Weight of PVC</b>	145	g/sq.m	DIN53352 BS3424 method5B
<b>Tensile strength</b>	Warp : 1180	N/5cm	DIN53354 BS3424 method6A
	Weft : 1030		
<b>Tearing strength</b>	Warp : 60	N	DIN53356 BS3424 method 7A
	Weft : 50		
<b>Adhesion</b>	60	N/5cm	DIN53357 BS3425 method9B
<b>Suitable temperature</b>	-20 -----+70	°C	DIN 53372 BS3424 method10
<b>Flame retardancy</b>	As requested.		
<b>Standard rolls:</b>	1,10 / 1,37 / 1,52 x 50 m		
<b>Printer type:</b>	Solvent / Eco-solvent / UV printers.		

**The indexes above are on average, so there will be ±5% tolerance for actual material.**

[www.integart.com.pl](http://www.integart.com.pl)

**Błonie k/Wrocławia**  
 tel. +48 71 315 31 91  
 biuro@integart.com.pl

**Bielsko-Biała**  
 tel. +48 33 817 19 16  
 bielsko@integart.com.pl

**Bydgoszcz**  
 tel. +48 52 327 45 00  
 bydgoszcz@integart.com.pl

**Gdańsk**  
 tel. +48 58 554 15 24  
 gdansk@integart.com.pl

**Katowice**  
 tel. +48 32 209 59 19  
 katowice@integart.com.pl

**Kraków**  
 tel. +48 12 653 43 92  
 krakow@integart.com.pl

**Łódź**  
 tel. +48 42 633 95 55  
 lodz@integart.com.pl

**Opole**  
 tel. +48 77 474 86 24  
 opole@integart.com.pl

**Poznań**  
 tel. +48 61 867 61 50  
 poznan@integart.com.pl

**Poznań – Krzesiny**  
 tel. +48 61 843 91 55  
 poznan2@integart.com.pl

**Toruń**  
 tel. +48 56 655 37 57  
 torun@integart.com.pl

**Wałbrzych**  
 tel. +48 74 665 96 06  
 walbrzych@integart.com.pl

**Warszawa – Jawczyce**  
 tel. +48 22 846 33 06  
 jawczyce@integart.com.pl

**Wrocław**  
 tel. +48 71 350 38 58  
 wroclaw@integart.com.pl