

Technical information: Steiko 41 – monomeric perforated film

specification	description	
PVC	type	calendered monomeric soft PVC film
	thickness	140 ± 10 µm
	color	white
	back	black
	shrinkage	≤ 0,7%
	opacity	> 99%
	holes no.	average 130 holes/sq in
	hole diameter	1,62 mm
	distance between holes	left-right 1,25 mm up-down 2,0 mm
	hole space	40%
adhesive	type	clear solvent based removable pressure sensitive glue
	weight	25 ± 5 (g/m ²)
	adhesion temperature	10°C ~ 40°C
	180° peeling force	≥ 5N / 25 mm (FTM1)
	initial adhesion	≥ 3N / 25 mm (FTM9)
	holding power	≥ 1440 min. (FTM8)
liner	type	kraft paper
	color	white
	weight	140 g ± 10 g/m ²
	release Force	0,05~0,25 N/25mm
storage period	12 months under ordinary condition at temperature of 22°C and relative humidity of 50-55%	
application	Outdoor digital and silk screen printing media for vehicle graphics, airport graphics, subway window, platform graphics, glass walls of building and signage display applications.	
printing methods	HP Latex / ecosolvent / solvent	
rolls	0,98 / 1,05 / 1,27 / 1,37 / 1,52 x 50 m	

The information contained in the product data sheet is based on practical knowledge and experience and should be used only as a source of information and does not constitute a legal guarantee of specific features. All information provided is for product description only and should not be considered as guaranteed properties in a legal sense. Due to the very large number of possible applications, the user should test the material for his own needs before final use. The buyer bears all risks associated with the use, handling and application of the material. We are liable for damages only up to the purchase price, excluding indirect and incidental damages.