Technical information: **SteikoTex Mesh Flag 115 FR**

PROPERTIES	DATA	TEST METHOD
surface	semi-glossy	N/A
total weight	115 g/m2	DIN EN ISO 2286-2, ASTM D751
base fabric	100% polyester	DIN 60001, ASTM D7641
weave method	warp-knitted	N/A
shrinkage	≤2%	ISO 9866-2-1991
flame resistance	B1	EN13501-1:2018
recommend fixation temperature	190°C, 30s	N/A
air permeability	4010 L/m2/S	N/A
rolls	1,60 / 1,83 x 100 m	
INK printability	DYE direct / DYE paper	

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%.

The information contained in the product data sheet is based on practical knowledge and experience and should be used only as a source of information and does not constitute a legal guarantee of specific features. All information provided is for product description only and should not be considered as guaranteed properties in a legal sense. Due to the very large number of possible applications, the user should test the material for his own needs before final use. The buyer bears all risks associated with the use, handling and application of the material. We are liable for damages only up to the purchase price, excluding indirect and incidental damages.