

# PRODUCT DATA SHEET

## Avery Dennison® Avery Dennison® MPI™ 3020 Matt High Opacity Series

Issued: 04/2021

### Introduction

Avery Dennison Multi Purpose Inkjet 3020 High Opacity series (HOP) films are matt white, self-adhesive short-term calendared vinyls with high opacity properties, offering a choice between permanent and removable adhesives.

MPI 3020 Matt HOP film features such as high opacity (above 99%), clear permanent and removable adhesive and good printability with attractive whiteness make it an optimal solution for a wide range of short-term, promotional applications, allowing customers to significantly reduce their inventory.

MPI 3024 HOP Easy Apply, part of MPI 3020 HOP series, is using Easy Apply technology allowing fast and easy bubble free application for effective promotions and short-term flat applications.

### Conversion

MPI 3020 Matt HOP series films are multi-purpose vinyls, suitable for a variety of wide format inkjet printers using hard solvent, eco/mild solvent, UV-curing or latex inks.

To enhance colour and to protect images against UV radiation and abrasion, it is recommended to protect Avery Dennison MPI 3020 Matt HOP series films using an overlaminate or varnish. For recommended combinations of DOL films and media, please refer to "Technical Bulletin 5.3. Recommended combinations of Avery Dennison® Overlaminates and Avery Dennison® Digital Print Media".

### Recommendations

- » Interior & exterior signs, including over posting applications
- » Window decoration
- » Promotional, point of sale, advertising applications on flat surfaces

### Features

- » Excellent printability and handling on selected printers
- » Superior whiteness and high opacity properties film
- » Easy cutting and application on a wide variety of substrates
- » High opacity film with clear permanent or removable adhesive constructions allow to cover a wide range of applications and significantly reduce customer inventory
- » MPI 3024 HOP Easy Apply enabling fast and easy application, cover-up performance for effective promotions.



#### Face Film

**MPI 3020/3021 Matt HOP** 95 micron matt white high opacity

**MPI 3024 Matt HOP EA** 95 micron matt white high opacity



#### Adhesive

**MPI 3020 HOP** Permanent, clear, acrylic based

**MPI 3021 HOP** Removable, clear, acrylic based

**MPI 3024 HOP** EA Permanent, clear, acrylic based



#### Backing

**MPI 3020/3021 HOP** Clay coated kraft paper, 125 g/m2

**MPI 3024 HOP EA** Clay coated kraft paper with air egress channels, 136 g/m2



#### Durability

3 years



#### Shelf Life

2 years

## Physical Characteristics

Features	Test method <sup>1</sup>	Results
Caliper, face film	ISO 534	95 micron
Dimensional stability	FINAT FTM 14	0.3 mm max.
Opacity	ISO 2471	> 99 %*
* Not a blackout film, opacity on par with MPI 3022/3023		
<b>MPI 3020 HOP</b>		
Adhesion, initial	FINAT FTM-1, stainless steel	480 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	750 N/m
<b>MPI 3021 HOP</b>		
Adhesion, initial	FINAT FTM-1, stainless steel	140 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	250 N/m
<b>MPI 3024 HOP EA</b>		
Adhesion, initial	FINAT FTM-1, stainless steel	310 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	465 N/m
Flammability		Self extinguishing
Shelf life	Stored at 22° C/50-55 % RH	2 years
Durability, unprinted	Vertical exposure	3 years
<b>Temperature range</b>		
<b>Features</b>		<b>Results</b>
Minimum application temperature:		≥ 10° C
Temperature range:		- 40 to +85 °C

**NOTE:** Materials have to be properly dried before further processing, for example laminating, varnishing or application. The residual solvents could change the products' specific features.

For good print and converting result we recommend to let the rolls acclimatize in the print/lamination room at least 24 hours before printing or converting. Too much temperature or humidity deviation between material and room climate can cause layflatness and/or printability issues.

Generally, constant material storage conditions of ideally 20°C (+/-2°C) /50% RH (+/- 5%), without too big climate deviations, will support a more robust and stable printing/converting process. For further details, please refer to TB 1.11.

## Important

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

*Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.*

*Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.*

*© 2021 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.*