



▶ DPF 4600GT Vinyl Film

High Performance, Digital Print Pressure-Sensitive Vinyl Film

DPF 4600GT is constructed of a 3.2 mil (80 micron) white gloss high performance film with a repositionable tinted adhesive system. The repositionable light gray adhesive allows for easy installation while ensuring enough opacity for covering up existing graphics or dark substrates. DPF 4600GT works great for vehicle decal and general signage. DPF 4600GT is rated for outdoor durability up to 5 years (unprinted). Printed durability is dependent on the ink system used.

APPLICATIONS & FEATURES

- Printable on Solvent, Eco-Solvent, Latex and UV digital printers.
- Great for medium-term graphics and vehicle decals.
- Recommended laminates: Series 3220, Series 3210 or Series 3420.

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	80% to 90%	
THICKNESS	Micrometer, Federal Bench Type	3.2-mil (80 micron)	
TENSILE STRENGTH	Tensile Tester 2-in (51mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s)	≥ 14 lb/in	≥ 2.5 kg/cm
ELONGATION	Instron Tensile Tester as above	≥ 180%	
SHELF LIFE	Free from excessive moisture, temperature, direct sunlight	1 year from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	60°F to 80°F	10°C to 32°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-20°F to 150°F	-29°C to 65°C
DIMENSIONAL STABILITY	Shrinkage After 158°F (70°C), 48 hours aging	15 mil	0.38 mm
PEEL ADHESION	PSTC-1, 15 min, RT 70°F (21°C)	≥ 3.9 lb/in	≥ 0.70 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	30 g/2 in	12 g/cm

*Standard Terms & Conditions Apply

USE & APPLICATION

DPF 4600GT will resist weathering best when applied to vertical or upper outboard angles. Horizontal angles, such as hood and auto roof surfaces, will deteriorate more quickly than vertical. This is due to increased exposure to sun and moisture, as well as high deposition of dirt and atmospheric contaminants. Actual horizontal weathering will be dependent on maintenance, location and elemental exposure. Use heat and/or chemical when removing image from vehicle (see Installer Handbook for details).

DPF 4600GT is designed to be used for vehicle graphics and wraps with flat or simple curves. When wrapping curves and channels with DPF 4600GT it is recommended the product be draped and not stretched into areas with channels.

APPLICATION	RECOMMENDED	NOT RECOMMENDED	LAMINATE
VEHICLE/FLEET DECALS	X		SERIES 3220, SERIES 3210 OR SERIES 3420
FLAT VEHICLE SIDES	X		SERIES 3220 OR SERIES 3210
SIMPLE CURVES	X		SERIES 3220 OR SERIES 3210
DEEP CHANNELS		X	
COMPLEX CURVES		X	
RIVETS		X	
MULTI-PURPOSE FLAT APPLICATIONS	X		SERIES 3220, SERIES 3210 OR SERIES 3420
MEDIUM-TERM STATIC SIGNAGE	X		SERIES 3220, SERIES 3210 OR SERIES 3420

GLOSSARY OF APPLICATION TERMS

Simple Curves - Defined as a slight stretch to the film in one direction (example: the side vehicle).

Complex Curves - Defined as extensive stretching (with or without heat) of material in multiple directions (example: bumpers).

Deep Channel - Channels in excess of a quarter inch in depth that require a “bridge and stretch” method for application.

TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller’s and manufacturer’s only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

August 2014