

TECHNICAL DATA

The indexes above are on average, so there will be $\pm 5\%$ tolerance for actual material.

Description of commodity: Coated blackout 440g 250*250 36*36			
ITEM	DATA	UNIT	TEST METHOD
Fabric	High tenacity yarns 100%PES(250D*250D)		DIN EN ISO2060
Construction	Weaving 36*36	inch	DIN60001
Total weight	440	g/sq.m	DIN53352 BS3424 method5A
Weight of fabric	78	g/sq.m	DIN53352 BS3424 method5B
Weight of pvc coating	362	g/sq.m	DIN53352 BS3424 method5B
Tensile strength	Warp: 1300	N/5cm	DIN53354 BS3424 method6A
	Weft: 1100		
Tearing strength	Warp: 70	N	DIN53356 BS3424 method 7A
	Weft: 60		
Adhesion	80	N/5cm	DIN53357 BS3425 method9B
Suitable temperature	-20 -----+70	°C	DIN 53372 BS3424 method10
Flame retardancy	NO		
Lacquering	NO		